



ISO TEST 354 AMIGA CURTAIN




Practical sound absorption coefficient according to ISO 11654 $\alpha_w = 0,60$ absorption class: C.
With folds + 100% at a distance of 10 cm from the wall.

ISO TEST 354 KASSAVA CURTAIN



Practical sound absorption coefficient according to ISO 11654 $\alpha_w = 0,60$ absorption class: C.
With folds + 100% at a distance of 10 cm from the wall.

ISO TEST 354 WOOL CURTAIN



Practical sound absorption coefficient according to ISO 11654 $\alpha_w = 0,75$ absorption class: C.
With folds + 100% (length: 7.20 m) at a distance of 15 cm from the wall.